



MEGHMANI

Megavat Dyestuff

Product Name

		YELLOW 5G High Conc. 0.5% 2.5%
		YELLOW 3RT Powder 0.5% 2.5%
		ORANGE RRT Microdisperse 1.0% 5.0%
		RED 3B Powder Fine 0.75% 3.0%
		RED 6B Microdisperse 0.5% 2.5%
		PURPLE 2R High Conc. 0.25% 1.25%
		DARK BLUE 2R Powder 0.5% 2.5%
		NAVY BLUE BR Microdisperse 1.0% 5.0%

C. I. No. Vat	Dyeing Method		Colour of Reduced Vat	Reducing Temp.	FASTNESS PROPERTIES										
	Suggested	Alternate			Light (1/1)	Severe Washing	Hypochlorite	Peroxide	Mercerising	Hot Pressing		Water Spotting		Dry cleaning	
										Immediate	After 4 hours	Immediate	After drying		
Yellow 2	A : 50°C	B : 50°C	Violet	50°C	4	4-5	5	4-5	+4-5	4-5	5	5	5	5	4-5
Orange 11	B : 50°C	B : 50°C	Reddish Orange	50°C	6-7	4	5	4-5	+4-5	3-4 G	5	4-5	5	5	4-5
Orange 2	A : 60°C	B : 50°C	Red Violet	60°C	5-6	4-5	4-5	4-5	+5	3Y	5	4Y	5	5	4-5
Red 10	B : 50°C	B : 50°C	Dull Olive	50°C	6	4-5	5	5	5	3-4	5	4	5	5	4-5
Red 13	A : 60°C	B : 50°C	Greenish Blue	60°C	6	4-5	5	5	+5	4-5Y	5	5	5	5	4-5
Violet 1	A : 50°C	B : 50°C	Blue	50°C	6	4-5	5	5	+4	3B	3B	2-3 R	5	5	4 R
Blue 20	A : 60°C	B : 50°C	Violet	60°C	6-7	4	5	4-5	+4-5R	3-4 R	5	3-4 R	5	5	4 R
Blue 18	A : 60°C	B : 50°C	Violet	60°C	6-7	5	5	4-5	+4-5	3-4	5	3-4 R	5	5	4 B



MEGHMANI

Megavat Dyestuff

Product Name

		BLUE DB Microdisperse 1.0% 4.0%
		BLUE GCDN Powder 0.5% 2.5%
		BLUE 3R High Conc. 0.5% 2.5%
		BLUE BC High Conc. 0.5% 2.5%
		BRILL BLUE RCL Microdisperse 1.0% 5.0%
		BLUE RSNR Powder 0.5% 2.5%
		DARK BLUE BOA Powder 0.5% 2.5%
		PEACOCK BLUE G Powder 0.5% 2.5%

C. I. No. Vat	Dyeing Method		Colour of Reduced Vat	Reducing Temp.	FASTNESS PROPERTIES									
	Suggested	Alternate			Light (1/1)	Severe Washing	Hypochlorite	Peroxide	Mercerising	Hot Pressing		Water Spotting		Dry cleaning
										Immediate	After 4 hours	Immediate	After drying	
.	A : 60°C	B : 50°C	Violet	60°C	6-7	4	5	4-5	+4-5R	3-4 B	5	3-4 R	5	4 R
Blue 14	A : 60°C	B : 50°C	Blue	60°C	7-8	4-5	2	4-5	+3-4G	4 G	5	4-5 R	5	4-5
Blue 4	A : 60°C	B : 50°C	Greenish Blue	60°C	7	4-5	2	5	+3 G	4 G	5	4-5	5	4-5
Blue 6	B : 50°C	B : 50°C	Blue	60°C	7-8	4-5	3	4-5	+4-5Y	4Y	4-5	4-5	5	4-5
.	A : 50°C	B : 50°C	Blue	60°C	7	4-5	3	4-5	+4-5Y	4Y	4-5	4 R	5	4-5
.	A : 50°C	B : 50°C	Blue	60°C	7	4-5	2	4-5	+3 G	4-5 G	5	4-5 R	5	4-5
.	A : 60°C	B : 50°C	Violet	60°C	7	4-5	4-5	4-5	+4-5R	3-4 B	5	3-4 R	5	4 R
.	A : 50°C	B : 50°C	Blue	60°C	7	4-5	3	4-5	+4-5Y	4Y	4-5	4 R	5	4-5

Megavat Dyestuff
Product Name

		JADE GREEN XBN High Conc. 0.5% 1.25%
		JADE GREEN 2G Powder 0.5% 2.5%
		JADE GREEN B High Conc. 0.25% 1.25%
		JADE GREEN 4G Powder 0.5% 2.5%
		BROWN R High Conc. 0.5% 2.5%
		BROWN BR High Conc. 0.5% 2.5%
		BROWN G High Conc. 0.5% 2.5%
		BROWN 2G High Conc. 0.5% 0.5%

C. I. No. Vat	Dyeing Method		Colour of Reduced Vat	Reducing Temp.	FASTNESS PROPERTIES									
	Suggested	Alternate			Light (1/1)	Severe Washing	Hypochlorite	Peroxide	Mercerising	Hot Pressing		Water Spotting		Dry cleaning
										Immediate	After 4 hours	Immediate	After drying	
Green 1	A : 60° C.	B : 50° C.	Blue	60° C.	7	4-5	4-5	5	+4-5	3B	4-5	4-5Y	5	4-5
Green 2	B : 60° C.	B : 50° C.	Blue	60° C.	6-7	4-5	4-5	5	+4-5	3B	4-5	4-5	5	4-5
Green 1.1	A : 60° C.	B : 50° C.	Blue	60° C.	5-6	4-5	4-5	4-5	+5	3Y	5	4Y	5	4-5
.	B : 60° C.	B : 30° C.	Blue	60° C.	6	4-5	4-5	5	+4-5	4B	5	5	5	4-5
Brown 3	A : 50° C.	B : 50° C.	Red Brown	50° C.	7	5	5	4-5	+4-5	4-5R	5	4-5	5	4-5
Brown 1	A : 50° C.	B : 50° C.	Yellow Brown	50° C.	7	5	5	5	+4-5	4-5	5	4B	5	4-5
.	A : 50° C.	B : 50° C.	Red Brown	50° C.	6	4-5	5	5	+4-5	4R	5	1-5	5	4
.	A : 50° C.	B : 50° C.	Red Brown	50° C.	6-7	4-5	4-5	5	+4-5	4-5R	5	4-5	5	4-5



MEGHMANI

Megavat Dyestuff

Product Name

		KHAKHI ECL Powder 0.1% 0.5%
		KHAKHI ECC Powder 0.1% 0.5%
		OLIVE GREEN B High Conc. 0.5% 2.5%
		OLIVE R High Conc. 0.5% 2.5%
		OLIVE D High Conc. 0.5% 2.5%
		GREY 2B Powder 0.5% 2.5%
		GREY 3B High Conc. 0.5% 1.25%
		GREY 4B Microdisperse 0.5% 2.5%

C. I. No. Vat	Dyeing Method		Colour of Reduced Vat	Reducing Temp.	FASTNESS PROPERTIES										
	Suggested	Alternate			Light (1/1)	Severe Washing	Hypochlorite	Peroxide	Mercerising	Hot Pressing		Water Spotting		Dry cleaning	
										Immediate	After 4 hours	Immediate	After drying		
-	A: 60°C	B: 50°C	Black Brown	60°C	6-7	4-5	4	4-5	+4-5	4Y	5	5	5	5	4
-	A: 60°C	B: 50°C	Brown	60°C	7	4-5	4	4-5	3-4	2-3 R	4 R	3-4	5	4-5	
Green 3	A: 60°C	B: 50°C	Blue Black	60°C	7	4	5	5	+4-5Y	4Y	5	4-5	5	4-5	
Black 27	A: 50°C	B: 50°C	Red Brown	50°C	6-7	4-5	4-5	4-5	+3-4Y	2-3 R	4 R	3-4Y	5	4-5	
Black 25	A: 60°C	B: 50°C	Black Brown	60°C	6-7	4-5	4	4-5	+4-5	4Y	5	5	5	4	
-	A: 60°C	B: 50°C	Dull Green	60°C	6	4-5	4-5	4-5	+4-5	4 R	5	4-5	5	4-5	
Black 16	A: 50°C	B: 50°C	Violet	50°C	6-7	4 R	3 R	4 R	4-5	4	5	4-5	5	4-5	
-	A: 60°C	B: 50°C	Dull Green	60°C	6	4-5	4-5	4-5	+4-5	3-4 B	5	4-5	5	4-5	

